

METALFLEX


Heat transfer flex-film

> for plotter-cutting

Cut 




Gold




Orange Copper



Red




Green



Blue



Silver



Gun Metal



MetalFlex is a 100% PU film. Light, very stretchable and with a beautiful metallic effect. You will never have to worry about washing a metallic heat transfer film because **MetalFlex** brings you an excellent 40 °C washing fastness.



MetalFlex est un film 100 % PU, très élastique et d'un bel effet métal. Vous n'aurez plus à vous soucier du lavage d'un transfert métallique puisqu'il offre une résistance au lavage à 40 °C.



MetalFlex ist 100% PU-Film. Weich, sehr elastisch mit einem brillanten Metalleffekt. Sie müssen sich nie wieder Sorgen über das Waschen von Metallfolien machen, denn **MetalFlex** besitzt eine hervorragende 40 °C Waschechtheit.



Manufacturing processes and related products are protected by existing patents :

FR 97 12921 ; EUR 98 402 542.9 ; US 6.224.707 ; FR 98 12862 ; EUR 99 402 398.4 ; US 6.249.297 ;
FR 04 08625 ; FR 05 05379 ; FR 05 05380 ; international extensions and new applications pending.

METALFLEX

Heat transfer flex-film

> for plotter-cutting

Cut



1



Scan or create a digital vector image.

2



Cut a mirror-image of your design on a plotter-cutting machine.

3



Apply with an electric press

COMPOSITION

Base	Hotmelt film (polyurethane)
Thickness	50 µ



TECHNICAL INFO

Washing fastness	up to 40°C (104°F) using mild detergents only
Transfer	15 - 17 seconds / 160 - 170°C (320-340°F) Low / medium pressure Please note that waiting 20 seconds to remove the liner after pressing will give a shinier finish

APPLICATION

Cotton
Poly/Cotton
Polyester

PACKAGING

	
49 cm (19")	5 meters (5,45 yd)
49 cm (19")	10 meters (10,9 yd)
49 cm (19")	25 meters (27,3 yd)



110 Bd Denis-Papin - 53000 LAVAL - France
Tél : 33 (0) 2 43 53 36 48 - Fax : 33 (0) 2 43 67 11 78
Email : contact@sef-france.com

www.sef-france.com